

IN THE CLAIMS

1. (previously presented) A composite sheet material comprising:

at least one porous core layer comprising at least one thermoplastic material and from about 20 weight percent to about 80 weight percent reinforcing fibers based on a total weight of said porous core layer, said porous core layer having a void content of about 5 percent to about 95 percent; and

at least one skin, each said skin covering at least a portion of a surface of said at least one porous core layer, said skin comprising at least one of a thermoplastic film, an elastomeric film, a thermosetting coating, an inorganic coating, a fiber based scrim, a non-woven fabric, and a woven fabric, said skin having a limiting oxygen index greater than about 22, as measured per ISO 4589.

2. (previously presented) A composite sheet material in accordance with Claim 1 wherein said thermoplastic film comprises at least one of poly(ether imide), poly(ether ketone), poly(ether-ether ketone), poly(phenylene sulfide), poly(arylene sulfone), poly(ether sulfone), poly(amide-imide), poly(1,4-phenylene), polycarbonate, nylon, and silicone.

3. (original) A composite sheet material in accordance with Claim 1 wherein said fiber based scrim comprises at least one of glass fibers, aramid fibers, graphite fibers, carbon fibers, inorganic mineral fibers, metal fibers, metalized synthetic fibers, and metalized inorganic fibers.

4. (original) A composite sheet material in accordance with Claim 3 wherein said fiber based scrim comprises at least one of polyacrylonitrile, p-aramid, m-aramid, poly(p-phenylene 2,6, benzobisoxazole), poly(ether-imide) and poly(phenylene sulfide).

5. (previously presented) A composite material in accordance with Claim 1 wherein said thermosetting coating comprises at least one of unsaturated polyurethanes, vinyl esters, phenolics and epoxies.

6. (original) A composite material in accordance with Claim 1 wherein said inorganic coating comprises minerals containing cations selected from Ca, Mg, Ba, Si, Zn, Ti and Al.

7. (original) A composite material in accordance with Claim 6 wherein said inorganic coating comprises at least one of gypsum, calcium carbonate and mortar.

8. (original) A composite sheet material in accordance with Claim 1 comprising:

a first porous core layer having a first surface and a second surface; and

at least one skin covering at least a portion of at least one of said first and second surface.

9. (original) A composite sheet material in accordance with Claim 1 comprising:

a first and a second porous core layer, each said core layer comprising a first and a second surface, said second surface of said first core layer positioned adjacent said first surface of said second core layer; and

at least one skin covering at least a portion of at least one of said first and second surfaces of said first core layer and said first and second surface of said second core layer.

10. (original) A composite sheet material in accordance with Claim 9 wherein said first porous core layer comprises at least one of a different thermoplastic material and a different fiber than said second porous core layer.

11. (original) A composite sheet material in accordance with Claim 1 comprising:

a first, a second, and a third porous core layer, each said core layer comprising a first and a second surface, said second surface of said first core layer positioned adjacent said

first surface of said second core layer, said second surface of said second core layer positioned adjacent said first surface of said third core layer; and

at least one skin covering at least one of said first and second surfaces of said first core layer, said first and second surface of said second core layer, and said first and second surface of said third core layer.

12. (original) A composite sheet material in accordance with Claim 11 wherein one of said porous core layers comprises at least one of a different thermoplastic material and a different fiber than at least one of said other layers.

13. (previously presented) A method of manufacturing a porous fiber-reinforced thermoplastic sheet, said method comprising:

providing a porous fiber-reinforced thermoplastic sheet comprising at least one porous core layer comprising a thermoplastic material and from about 20 weight percent to about 80 weight percent reinforcing fibers, each porous core layer having a void content of about 5 percent to about 95 percent; and

laminating at least one skin to a surface of the porous fiber-reinforced thermoplastic sheet, each skin comprising at least one of a thermoplastic film, an elastomeric film, a thermosetting coating, an inorganic coating, a fiber based scrim, a non-woven fabric, and a woven fabric, the skin having a limiting oxygen index greater than about 22, as measured per ISO 4589 to enhance at least one of the flame, smoke, heat release and gaseous emissions characteristics of the porous fiber-reinforced thermoplastic sheet.

14. (original) A method in accordance with Claim 13 wherein the thermoplastic film comprises at least one of poly(ether imide), poly(ether ketone), poly(ether-ether ketone), poly(phenylene sulfide), poly(arylene sulfone), poly(ether sulfone), poly(amide-imide), poly(1,4-phenylene), polycarbonate, nylon, and silicone.

15. (original) A method in accordance with Claim 13 wherein the fiber based scrim comprises at least one of glass fibers, aramid fibers, graphite fibers, carbon fibers, inorganic mineral fibers, metal fibers, metalized synthetic fibers, and metalized inorganic fibers.

16. (original) A method in accordance with Claim 15 wherein the fiber based scrim comprises at least one of polyacrylonitrile, p-aramid, m-aramid, poly(p-phenylene 2,6, benzobisoxazole), poly(ether-imide) and poly(phenylene sulfide).

17. (previously presented) A method in accordance with Claim 13 wherein the thermosetting coating comprises at least one of unsaturated polyurethanes, vinyl esters, phenolics and epoxies.

18. (original) A method in accordance with Claim 13 wherein the inorganic coating comprises minerals containing cations selected from Ca, Mg, Ba, Si, Zn, Ti and Al.

19. (original) A method in accordance with Claim 18 wherein the inorganic coating comprises at least one of gypsum, calcium carbonate and mortar

20. (original) A method in accordance with Claim 13 wherein said providing a porous fiber reinforced thermoplastic sheet comprises providing a porous fiber reinforced thermoplastic sheet comprising a first porous core layer having a first surface and a second surface, and said laminating at least one skin comprises laminating at least one skin covering at least one of said first and second surface.

21. (original) A method in accordance with Claim 13 wherein said providing a porous fiber reinforced thermoplastic sheet comprises providing a porous fiber reinforced thermoplastic sheet comprising a first and a second porous core layer, each core layer comprising a first and a second surface, the second surface of the first core layer positioned adjacent the first surface of the second core layer, and said laminating at least one skin comprises laminating at least one skin covering at least one of the first and second surfaces of the first core layer and the first and second surface of the second core layer.

22. (original) A method in accordance with Claim 13 wherein said providing a porous fiber reinforced thermoplastic sheet comprises providing a porous fiber reinforced thermoplastic sheet comprising a first, a second, and a third porous core layer, each core layer comprising a first and a second surface, the second surface of the first core layer positioned adjacent the first surface of the second core layer, the second surface of the second core layer positioned adjacent the first surface of the third core layer, and said laminating at least one skin comprises laminating at least one skin covering at least one of the first and second surfaces of the first core layer, the first and second surface of the second core layer, and the first and second surface of the third core layer.

23. (currently amended) A method in accordance with Claim 13 wherein the skin ~~comprise~~ comprises at least one of a fiber based scrim, a non-woven fabric and a woven fabric.

24. (previously presented) A composite sheet material comprising:

a permeable core comprising discontinuous reinforcing fibers bonded together with a thermoplastic resin, said permeable core having a density from about 0.2 gm/cc to about 1.8 gm/cc, and a void content of about 5 percent to about 95 percent, said permeable core including a surface region; and

an adherent layer adjacent to said surface region, said adherent layer comprising a material having a limiting oxygen index greater than about 22, as measured per ISO 4589.

25. (original) A composite sheet material according to Claim 24 wherein said permeable core has an open cell structure.

26. (original) A composite sheet material according to Claim 24 wherein said permeable core comprises at least one of metal fibers, metalized inorganic fibers, metalized synthetic fibers, glass fibers, graphite fibers, carbon fibers, ceramic fibers, and aramid fibers.

27. (original) A composite sheet material according to Claim 24 wherein said permeable core comprises a thermoplastic resin selected from the group consisting of

polyethylene, polypropylene, polystyrene, acrylonitrilstyrene, butadiene, polyethyleneterephthalate, polybutyleneterephthalate, polybutyleneterachlorate, polyvinyl chloride, polyphenylene ether, polycarbonates, polyester carbonates, thermoplastic polyesters, polyetherimides, acrylonitrile-butylacrylate-styrene polymers, amorphous nylon, polyarylene ether ketone, polyphenylene sulfide, polyaryl sulfone, polyether sulfone, poly(1,4 phenylene) compounds, silicones and mixtures thereof.

28. (original) A composite sheet material according to Claim 24 wherein said core comprises from about 20 to about 80 percent by weight fibers and from about 20 to about 80 percent by weight of a thermoplastic resin.

29. (original) A composite sheet material according to Claim 24 wherein said core comprises from about 35 to about 55 percent by weight fibers and from about 45 to about 65 percent by weight of a thermoplastic resin.

30. (original) A composite sheet material according to Claim 24 wherein said composite has a four minute smoke density,  $D_s$ , of less than about 200 when tested in accordance with ASTM E662.

31. (original) A composite sheet material according to Claim 26 having a thickness from about 0.5 mm to about 25 mm.

32. (original) A composite sheet material according to Claim 26 wherein said adherent layer has a thickness from about 25 micrometers to about 2.5 mm.

33. (previously presented) A composite sheet material according to Claim 26 wherein said adherent adjacent layer comprises at least one of a thermoplastic film, an elastomeric film, a thermosetting coating, an inorganic coating, a fiber based scrim, a non-woven fabric, and a woven fabric, said skin having a limiting oxygen index greater than about 22, as measured per ISO 4589.

34. (original) A composite sheet material in accordance with Claim 33 wherein said thermoplastic film comprises at least one of poly(ether imide), poly(ether ketone),

poly(ether-ether ketone), poly(phenylene sulfide), poly(arylene sulfone), poly(ether sulfone), poly(amide-imide), poly(1,4-phenylene), polycarbonate, nylon, and silicone.

35. (original) A composite sheet material in accordance with Claim 33 wherein said fiber based scrim comprises at least one of glass fibers, aramid fibers, graphite fibers, carbon fibers, inorganic mineral fibers, metal fibers, metalized synthetic fibers, and metalized inorganic fibers.

36. (original) A composite sheet material in accordance with Claim 33 wherein said fiber based scrim comprises at least one of polyacrylonitrile, p-aramid, m-aramid, poly(p-phenylene 2,6, benzobisoxazole), poly(ether-imide) and poly(phenylene sulfide).

37. (previously presented) A composite material in accordance with Claim 33 wherein said thermosetting coating comprises at least one of unsaturated polyurethanes, vinyl esters, phenolics and epoxies.

38. (original) A composite material in accordance with Claim 33 wherein said inorganic coating comprises of minerals containing cations selected from Ca, Mg, Ba, Si, Zn, Ti and Al.

39. (original) A composite material in accordance with Claim 38 wherein said inorganic coating comprises at least one of gypsum, calcium carbonate and mortar.

40. (previously presented) A composite sheet material in accordance with Claim 1 wherein said at least one porous core layer is formed by a process selected from the group consisting essentially of a wet laid process, an air laid process, a dry blend process, and a carding and needle process.

41. (previously presented) A method in accordance with Claim 13 wherein the porous fiber-reinforcing thermoplastic sheet is formed by a process selected from the group consisting essentially of a wet laid process, an air laid process, a dry blend process, and a carding and needle process.

42. (currently amended) A composite sheet material in accordance with Claim 24 wherein said [[at]] permeable core is formed by a process selected from the group consisting essentially of a wet laid process, an air laid process, a dry blend process, and a carding and needle process.